CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-31-86** **Date: 10/06/2019**

Customer : Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.

Address : T-Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15

Agency : Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.

Customer's Reference : EE/SWD/DHZ/WO/06/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 15-05-19

Customer ID : Drain Bottom Raft Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/06/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M25	13/05/2019	10/06/2019	151.37 X 151.38 X 149.55	22915	8.586	638.2	27.9	27.5
2	Drain Bottom Raft Concrete	M25	13/05/2019	10/06/2019	150.22 X 150.39 X 150.58	22592	8.206	598.8	26.5	
3	Drain Bottom Raft Concrete	M25	13/05/2019	10/06/2019	149.78 X 151.09 X 149.94	22632	8.245	639.0	28.2	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 20/05/2019

Lab ID	:	**CP-2020-01-31-86**
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	15-05-19
Customer ID	:	Drain Bottom Raft Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 20/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M25	13/05/2019	20/05/2019	151.80 X 149.16 X 149.68	22643	8.572	523.4	23.1	22.7
2	Drain Bottom Raft Concrete	M25	13/05/2019	20/05/2019	151.13 X 149.66 X 150.59	22618	8.136	517.5	22.9	
3	Drain Bottom Raft Concrete	M25	13/05/2019	20/05/2019	149.15 X 151.14 X 150.48	22543	8.791	501.3	22.2	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2020-01-31-86 **Date: 10/06/2019**

Customer : Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.

Address : T-Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15

Agency : Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.

Customer's Reference : EE/SWD/DHZ/WO/06/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 15-05-19

Customer ID : Drain Bottom Raft Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/06/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M25	13/05/2019	10/06/2019	149.20 X 150.87 X 149.28	22510	8.586	615.2	27.3	27.4
2	Drain Bottom Raft Concrete	M25	13/05/2019	10/06/2019	150.24 X 149.54 X 149.52	22468	8.206	584.9	26.0	
3	Drain Bottom Raft Concrete	M25	13/05/2019	10/06/2019	151.16 X 151.15 X 149.53	22848	8.245	660.6	28.9	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2020-01-31-86** **Date: 20/05/2019**
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	15-05-19
Customer ID	:	Drain Bottom Raft Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	20/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M25	13/05/2019	20/05/2019	151.86 X 150.16 X 150.69	22804	**8.572**	539.4	23.7	23.2
2	Drain Bottom Raft Concrete	M25	13/05/2019	20/05/2019	150.35 X 151.22 X 150.62	22736	**8.136**	520.4	22.9	
3	Drain Bottom Raft Concrete	M25	13/05/2019	20/05/2019	149.02 X 151.33 X 149.36	22550	**8.791**	517.1	22.9	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬೃಹತ್ ಮಳೆ ನೀರುಗಾಲುವೆ ಉಪ-ವಿಭಾಗ,
ದಾಸರಹಳ್ಳಿ ವಲಯ, ಬಿ.ಬಿ.ಎಮ್.ಪಿ. ಬೆಂಗಳೂರು

Page 1/1
****End of Report****

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 10/06/2019

Lab ID	:	CP-2020-01-31-86
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	15-05-19
Customer ID	:	Drain Bottom Raft Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	10/06/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M25	13/05/2019	10/06/2019	149.33 X 151.83 X 151.45	22674	8.586	620.6	27.4	27.4
2	Drain Bottom Raft Concrete	M25	13/05/2019	10/06/2019	149.84 X 149.82 X 151.96	22448	8.206	599.6	26.7	
3	Drain Bottom Raft Concrete	M25	13/05/2019	10/06/2019	149.96 X 151.91 X 149.57	22781	8.245	638.4	28.0	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 20/05/2019

Lab ID	:	**CP-2020-01-31-86**
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	15-05-19
Customer ID	:	Drain Bottom Raft Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	20/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M25	13/05/2019	20/05/2019	149.48 X 149.76 X 151.93	22386	8.572	516.0	23.1	22.8
2	Drain Bottom Raft Concrete	M25	13/05/2019	20/05/2019	151.82 X 150.19 X 149.10	22803	8.136	522.3	22.9	
3	Drain Bottom Raft Concrete	M25	13/05/2019	20/05/2019	149.93 X 149.20 X 149.46	22369	8.791	504.3	22.5	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-31-86** **Date: 10/06/2019**

Customer : Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.

Address : T-Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15

Agency : Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.

Customer's Reference : EE/SWD/DHZ/WO/06/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 15-05-19

Customer ID : Drain Bottom Raft Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/06/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Raft Concrete	M25	13/05/2019	10/06/2019	149.66 X 151.89 X 150.12	22733	8.586	624.2	27.5	27.2
2	Drain Bottom Raft Concrete	M25	13/05/2019	10/06/2019	151.06 X 149.16 X 151.06	22532	8.206	587.7	26.1	
3	Drain Bottom Raft Concrete	M25	13/05/2019	10/06/2019	149.77 X 149.22 X 150.27	22349	8.245	626.0	28.0	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 26/05/2019

Lab ID	:	**CP-2020-01-31-86**
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	21-05-19
Customer ID	:	Drain Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	26/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M25	19/05/2019	26/05/2019	150.26 X 149.50 X 149.60	22463	8.572	527.8	23.5	23.0
2	Drain Side Wall Concrete	M25	19/05/2019	26/05/2019	151.83 X 151.51 X 149.50	23004	8.136	525.9	22.9	
3	Drain Side Wall Concrete	M25	19/05/2019	26/05/2019	150.69 X 151.28 X 150.66	22796	8.791	515.8	22.6	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

CIVIL PRO

AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005

4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No : TC-6648

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 16/06/2019

Lab ID	:	CP-2020-01-31-86
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #11 No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562123.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	21-05-19
Customer ID	:	Drain Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	16/06/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M25	19/05/2019	16/06/2019	151.44 X 151.02 X 151.11	22871	8.586	632.4	27.7	27.6
2	Drain Side Wall Concrete	M25	19/05/2019	16/06/2019	149.96 X 149.91 X 150.71	22480	8.206	606.1	27.0	
3	Drain Side Wall Concrete	M25	19/05/2019	16/06/2019	151.12 X 151.46 X 149.94	22889	8.245	647.3	28.3	

Note:
The results pertain to the samples received and tested
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1

*****End of Report*****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 26/05/2019

Lab ID	:	CP-2020-01-31-86
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	21-05-19
Customer ID	:	Drain Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	26/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm²)	Average Compressive Strength (N/mm²)
1	Drain Side Wall Concrete	M25	19/05/2019	26/05/2019	151.27 X 150.99 X 151.17	22841	8.572	532.7	23.3	22.7
2	Drain Side Wall Concrete	M25	19/05/2019	26/05/2019	151.77 X 151.30 X 150.26	22963	8.136	512.6	22.3	
3	Drain Side Wall Concrete	M25	19/05/2019	26/05/2019	150.49 X 149.17 X 149.02	22447	8.791	506.2	22.6	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 16/06/2019

Lab ID	:	**CP-2020-01-31-86**
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	21-05-19
Customer ID	:	Drain Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	16/06/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M25	19/05/2019	16/06/2019	149.42 X 150.62 X 150.22	22506	8.586	627.7	27.9	27.9
2	Drain Side Wall Concrete	M25	19/05/2019	16/06/2019	149.40 X 150.30 X 149.85	22454	8.206	602.5	26.8	
3	Drain Side Wall Concrete	M25	19/05/2019	16/06/2019	150.12 X 151.44 X 150.00	22733	8.245	655.4	28.8	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 26/05/2019

Lab ID	:	**CP-2020-01-31-86**
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	21-05-19
Customer ID	:	Drain Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	26/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M25	19/05/2019	26/05/2019	150.07 X 150.85 X 151.90	22638	8.572	539.3	23.8	22.9
2	Drain Side Wall Concrete	M25	19/05/2019	26/05/2019	150.08 X 151.59 X 149.12	22751	8.136	512.8	22.5	
3	Drain Side Wall Concrete	M25	19/05/2019	26/05/2019	150.49 X 150.48 X 150.52	22646	8.791	506.8	22.4	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಟಿ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ,
ಗಾಯತ್ರಿ ವಲಯ, ಬಿ.ಬಿ.ಎಂ.ಪಿ. ಬೆಂಗಳೂರು

Page 1/1
****End of Report****

Scanned with CamScanner